

**Product Name** Silicone Sealant

**Product ID** 22010, 29186, 82000

## HIGH STRENGTH 1-PART INDUSTRIAL/CONSTRUCTION GRADE SILICONE SEALANT

Aquascape Silicone is a one component room temperature vulcanizing RTV acetoxy cure silicone sealant and adjesive that has been chemically formulated for high strength adhesion. When fully cured, this unique VOC compliant formula offers UV stability and excellent adhesion to form waterproof and airtight bonds to metal, steel, tile, fiberglass, ceramic, glass, aluminum, painted surfaces, wood, plywood, marble, plus many other common substrates. This product is specifically formulated to offer all weather performance to meet today's Green Building Standards.

## **FEATURES & BENEFITS**

## High Strength Excellent Weatherability UV Stable Non-Yellowing VOC Compliant Non-Flammable Waterproof Excellent Adhesion Non-Shrinking

## **CONSTRUCTION & INDUSTRIAL APPLICATIONS**

Sealing & Glazing
HVAC/R
Plumbing
Roofing
Kitchen and Bath
Countertops
Sanitary Seals
Precast Concrete
Transportation Seals
Marine Cabins
Appliance Trim
Interior/Exterior
Above Grade

**MEETS SPECIFICATIONS:** ASTM C920 type S, Grade NS, Class 25; TT-S-00230C, TT-S-01543A, MIL-A-46106A, FDA CFR 177.2600, USDA Approved, NSF 51, UL Recognized Component.

AVAILABLE COLORS: Clear, Black

	A	
Adnascape,	Aquascaper Black Silicon	Aquascape CLEAF SILICONE
BLACK SILLONE SEAMIT FOR FORDS - sha for for forms - sha for forms - sha for forms - forms or forms regist and - forms or forms regist and - forms or forms regist and - forms or forms register and - forms	Indicat for Pands  Cit by the  Cit by the  Service of the service of the service  Constitution of the s	School for Ponds School for Ponds School for Ponds School for School for School School for School School for School School for School School School for School
THE STATE OF THE S	E 87/005 10.1 R. O.L. (26.)	and the star and t

PHYSICAL PROPERTIES		TEST METHOD
Cure System	Acetoxy	
Movement Capability, %	±25%	ASTM C-719
Modulus	Medium	ASTM D-412
Physical Properties (Cured)	Rubber	
Specific Gravity	1.04	
Extrusion Rate, g/min.	370	ASTM C-1183
1/8" orifice @ 50 psi		Modified
Temperature Range	-62'F to 350'F	
Intermittent Temperature Range	400'F	
Accelerated Weathering (10,000 hrs.)	No Change	QUV Weatherometer
Skin Over Time (min)	10*	MNA Method
Tack Over Time (min)	17*	ASTM C-679
Cure Rate	1/8" per 24 hrs*	MNA Method
Tensile Strength (psi)	310	ASTM D-412
Elongation %	500	ASTM D-412
Durometer Shore A	26	ASTM C-661
Dielectric Strength kv/mm (v/mil)	20 (500)	
Dielectric Constant at 100 Hz	2.7 @ 60	
Shelf Life (months)	24	
Volatile Organic Content	30 gr./liter	